

## FLORIDA DEPARTMENT OF Environmental Protection

Marjory Stoneman Douglas Building 3900 Commonwealth Boulevard Tallahassee, FL 32399 Ron DeSantis Governor

Jeanette Nuñez Lt. Governor

Shawn Hamilton Secretary

**January 4, 2022** 

## NOTICE TO APPLICANTS ADDENDUM NO. THREE (3)

Highlands Hammock State Park – Residence Electrical & Plumbing Upgrades DEP Bid NO. BDC19-21/22

TO BIDDERS AND PLAN HOLDERS ON THE ABOVE REFERENCED PROJECT: PLEASE NOTE CONTENTS HEREIN AND INCLUDE WITH YOUR BID SUBMISSION.

## **NOTICE**

It will be required that this addendum be signed in acknowledgment of receipt and that it be included with your Bid when same is submitted to Debbie Boyette, Government Operations Consultant II, Bureau of Design and Construction, 3900 Commonwealth Blvd. MS520, Tallahassee, Florida 32399-3000. Failure to do so may be grounds for rejection of the Bid.

Signature of Contractor and Date

The Following statements supersede & supplement the corresponding items in the specifications & drawings:

The New VTRs and SK Routing are hereby incorporated into the bid package and supersede those originally posted with the bid documents. Due to size restrictions on the Vendor Bid System, these documents can be found on the plans website. Please contact the Bureau of Design and Construction's Contracts Section at Deborah.Boyette@FloridaDEP.gov with any questions.

The following changes have been made to the contract documents:

- The days to substantial completion are 120 days.
- Contractor to abate/remove asbestos containing floor material in kitchen and dining area of BL036001 and replace with new flooring.
- Roof and asbestos report
- New VTRs and SK Routing

In all other respects, the contract documents of which this is an Addendum, and attachments relative thereto, shall remain in full force and effect.							



## REPORT OF BULK SAMPLE ANALYSIS FOR ASBESTOS

TESTED FOR: PSI, Inc

5801 Benjamin Center Drive Suite 112

Tampa, FL 33634 Attn: Robert Mundy Michael Baker International

Project ID: 05523339-1

Highlands Hammock State Pa 8 Structures, Sebring, FL

Analyst:	D	an Anderson	Work Order:	2112443		Page: 1 of 1
Client ID	Lab ID (Layer)	Sample Description (Color, Texture, Etc.)  Analyst's Comment		Asbestos Content (Percent and Type)	Non-asbestos Fibers (Percent and Type)	
01	001A	<ul><li>(1) Black, Shingle, Homogen</li><li>(2) Black, Felt, Homogeneou</li></ul>		NO ASBESTOS DETECTED NO ASBESTOS DETECTED	10% 45%	Fibrous Glass Cellulose Fiber
02	002A	(1) Black, Shingle, Homogen (2) Black, Felt, Homogeneou		NO ASBESTOS DETECTED NO ASBESTOS DETECTED	10% 45%	Fibrous Glass Cellulose Fiber
03	003A	(1) Black, Shingle, Homogen (2) Black, Tar, Homogeneous		NO ASBESTOS DETECTED NO ASBESTOS DETECTED	10% No	Fibrous Glass one Reported
04	004A	(1) Black, Shingle, Homogen (2) Black, Tar, Homogeneous		NO ASBESTOS DETECTED NO ASBESTOS DETECTED		Fibrous Glass one Reported
05	005A	<ul><li>(1) Black, Shingle, Homogen</li><li>(2) Black, Tar, Homogeneous</li><li>(3) Black, Felt, Homogeneous</li></ul>	s	NO ASBESTOS DETECTED NO ASBESTOS DETECTED NO ASBESTOS DETECTED	10% No 45%	Fibrous Glass one Reported Cellulose Fiber
06	006A	<ul><li>(1) Black, Shingle, Homogen</li><li>(2) Black, Tar, Homogeneous</li><li>(3) Black, Felt, Homogeneous</li></ul>	s	NO ASBESTOS DETECTED NO ASBESTOS DETECTED NO ASBESTOS DETECTED	10% No 45%	Fibrous Glass one Reported Cellulose Fiber
07	007A	(1) Black, Shingle, Homogen (2) Black, Felt, Homogeneou		NO ASBESTOS DETECTED NO ASBESTOS DETECTED	10% 75%	Fibrous Glass Cellulose Fiber
08	A800	(1) Black, Shingle, Homogen (2) Black, Felt, Homogeneou		NO ASBESTOS DETECTED NO ASBESTOS DETECTED	10% 75%	Fibrous Glass Cellulose Fiber

Report Notes: (PT) Point Count Results

Quantitation is based on a visual estimation of the relative area of bulk sample components, unless otherwise noted in the "Comments" section of this report. The results are valid only for the item tested as received. This report may not be used to claim product endorsement by NVLAP or any agency of the U.S. Government. Method used: E.P.A. Interim Method for the Determination of Asbestos in Bulk Insulation Samples (EPA 600/M4-82-020). Polarized Light Microscopy is not consistently reliable in detecting asbestos in floor coverings and similar non-friable organically bound materials. Quantitative Transmission Electron Microscopy is currently the only method that can be used to determine if the material can be considered or treated as non-asbestos containing. Samples will be disposed of within 30 days unless notified in writing by the client. No part of this report may reproduced, except in full, without written permission of the laboratory. The reporting limit is 1% by weight. NVLAP Lab Code 101350-0.

Respectfully submitted,

PSI. Inc.

Approved Signatory
Cathy McNamee